

AMENDMENT UNDER 37 C.F.R. § 1.111  
U.S. Appl. 09/635,141

for extruding a material for forming a polyolefin non-foamed layer and at least one extrusion die for co-extruding the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer therethrough to form the multilayer polyolefin foamed sheet, the method comprising:

a melt kneading step in which, in the first extruder, a resin material for forming a polyolefin foamed layer is melted and the melted resin material for forming a polyolefin foamed layer and a foaming agent supplied from the foaming agent-supplying device are mixed to form the material for forming a polyolefin foamed layer;

a melting step in which the material for forming a polyolefin non-foamed layer is melted in the second extruder; and

a co-extruding step in which the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer in their melted states are co-extruded into atmospheric pressure through the extrusion die and the extruded material for forming a polyolefin foamed layer is foamed to form the multilayer polyolefin foamed sheet, and

wherein the co-extruding step is conducted under conditions satisfying the relationship of

$$10 \geq Q \text{ (kg/hr)}/W \text{ (mm)} \geq 0.3$$

wherein  $Q$  (kg/hr) denotes the amount of the resin to be extruded through the extrusion die and  $W$  (mm) denotes a die lip diameter.

6. (Amended) A method for producing a multilayer polyolefin foamed sheet comprising at least one polyolefin foamed layer and at least one polyolefin non-foamed layer, wherein the method uses a producing apparatus comprising at least one first extruder for extruding a material for forming a polyolefin foamed layer wherein the first extruder is equipped with a foaming

AMENDMENT UNDER 37 C.F.R. § 1.111  
U.S. Appl. 09/635,141

agent-supplying device for supplying a foaming agent to a cylinder, at least one second extruder for extruding a material for forming a polyolefin non-foamed layer and at least one extrusion die for co-extruding the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer therethrough to form the multilayer polyolefin foamed sheet, the method comprising:

a melt kneading step in which, in the first extruder, a resin material for forming a polyolefin foamed layer is melted and the melted resin material for forming a polyolefin foamed layer and a foaming agent supplied from the foaming agent-supplying device are mixed to form the material for forming a polyolefin foamed layer;

a melting step in which the material for forming a polyolefin non-foamed layer is melted in the second extruder; and

a co-extruding step in which the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer in their melted states are co-extruded into atmospheric pressure through the extrusion die and the extruded material for forming a polyolefin foamed layer is foamed to form the multilayer polyolefin foamed sheet, and

further comprising a laminating step for laminating at least one multilayer polyolefin foamed sheet produced.

19. (Amended) A method for producing a multilayer polyolefin foamed sheet comprising at least one polyolefin foamed layer and at least one polyolefin non-foamed layer, wherein the method uses a producing apparatus comprising at least one first extruder for extruding a material for forming a polyolefin foamed layer wherein the first extruder is equipped with a foaming agent-supplying device for supplying a foaming agent to a cylinder, at least one

AMENDMENT UNDER 37 C.F.R. § 1.111 }  
U.S. Appln. 09/635,141

second extruder for extruding a material for forming a polyolefin non-foamed layer and at least one extrusion die for co-extruding the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer therethrough to form the multilayer polyolefin foamed sheet, the method comprising:

A3  
could  
a melt kneading step in which, in the first extruder, a resin material for forming a polyolefin foamed layer is melted and the melted resin material for forming a polyolefin foamed layer and a foaming agent supplied from the foaming agent-supplying device are mixed to form the material for forming a polyolefin foamed layer;

a melting step in which the material for forming a polyolefin non-foamed layer is melted in the second extruder; and

a co-extruding step in which the material for forming a polyolefin foamed layer and the material for forming a polyolefin non-foamed layer in their melted states are co-extruded into atmospheric pressure through the extrusion die and the extruded material for forming a polyolefin foamed layer is foamed to form the multilayer polyolefin foamed sheet, and

further comprising a pressure reducing step for passing the extruded multilayer polyolefin foamed sheet through a vacuum chamber to increase an expansion ratio of the foamed layer.

A4  
28. (Amended) The method for producing a multilayer polyolefin foamed sheet according to claim 3, 6 or 19, further comprising an extending step for extending the co-extruded multilayer polyolefin foamed sheet in a direction perpendicular to the extruding direction by means of an extending device, wherein the extending step is conducted after the co-extruding step.

**Please add the following new claims:**

AZ  
48. (New) The method for producing a multilayer polyolefin foamed sheet according to claim 3, 6 or 19, wherein the extrusion die is a circular die and the material for forming a polyolefin foamed layer and the material for forming the polyolefin non-foamed layer are co-extruded into a cylindrical form in the co-extruding step.